



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification 5 :</b> A01N 1/02, C12P 1/00 C12N 5/00	<b>A1</b>	<b>(11) International Publication Number:</b> WO 93/18649 <b>(43) International Publication Date:</b> 30 September 1993 (30.09.93)
<b>(21) International Application Number:</b> PCT/US93/02609 <b>(22) International Filing Date:</b> 22 March 1993 (22.03.93)  <b>(30) Priority data:</b> 07/856,137 23 March 1992 (23.03.92) US  <b>(71) Applicant (for all designated States except US):</b> CLOVER CONSOLIDATED, LIMITED [CH/CH]; 37, avenue de Rumini, CH-1002 Lausanne (CH).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only) :</b> DESAI, Neil, P. [IN/US]; 847 Alandale Avenue, Los Angeles, CA 90071 (US). SOON-SHIONG, Patrick [US/US]; 11755 Chenault Street, Los Angeles, CA 90049 (US). SANDFORD, Paul, A. [US/US]; 2822 Overland Avenue, Los Angeles, CA 90064 (US). HEINTZ, Roswitha, E. [US/US]; 1940 Malcolm Avenue, Los Angeles, CA 90025 (US).		<b>(74) Agent:</b> REITER, Stephen, E.; Pretty, Schroeder, Brueggemann & Clark, 444 South Flower Street, Suite 2000, Los Angeles, CA 90071 (US).  <b>(81) Designated States:</b> AT, AU, BB, BG, BR, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> GRAFT COPOLYMERS OF POLYCATIONIC SPECIES AND WATER-SOLUBLE POLYMERS, AND USES THEREOF  <b>(57) Abstract</b>  In accordance with the present invention, there are provided methods to render cells non-adhesive and/or non-immunogenic with respect to macromolecules typically encountered in culture media or in physiological media.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

GRAFT COPOLYMERS OF POLYCATIONIC SPECIES AND  
WATER-SOLUBLE POLYMERS, AND USES THEREOF

The present invention relates to methods for rendering cells non-adhesive. In another aspect, the present invention relates to methods for rendering cells non-immunogenic. In yet another aspect, the present invention relates to methods for the stabilization of liposomes. In a further aspect, the present invention relates to methods for the *in vitro* generation of neural networks.

10

BACKGROUND OF THE INVENTION

Water-soluble polymers, such as polyethylene glycols (PEGs), have been investigated extensively in recent years for use as biocompatible, protein repulsive, noninflammatory, and nonimmunogenic modifiers for drugs, proteins, enzymes, and surfaces of implanted materials. These characteristics have variously been attributed to a combination of properties of such polymers, e.g., nonionic character, water solubility, backbone flexibility, and volume exclusion effect in solution or when immobilized on a surface.

While extensive efforts have been made to render foreign substances, such as drugs, proteins, and the like, non-immunogenic employing water-soluble polymers such as PEG, the use of such polymers to render an individual cell non-immunogenic has not been considered in the art. If such polymers could be attached directly to a cell surface, then it is possible, due to the exclusion of proteins and macromolecules from the vicinity of the cell surface, that the cell as a whole may be rendered non-immunogenic. The ability to accomplish such attachment would be invaluable for a variety of treatment protocols.

It is known that mammalian cell membranes have a variety of negatively charged species on their exterior. For example, negatively charged proteoglycans (PGA), glycosaminoglycans (GAG), such as chondroitin sulfate and heparin sulfate, and negatively charged lipids have all been identified on cell exteriors. Not surprisingly, polycation species such as polylysine and polyornithine interact with negatively charged cell surfaces to form a strong ionic linkage. Unfortunately, polycations (such as polylysine and polyornithine) are known to be cytotoxic, even at fairly low concentrations. Polylysine, for example, has been used as a cell fixative, and has been shown to cause cell aggregation (e.g., with human platelets).

15

While water-soluble polymers, having found use in a variety of biological applications, would be ideal for use in treating cells to render them non-immunogenic, their generally non-ionic nature renders them substantially unable to bind to cell membranes. Thus, for example, treatment of cells with unmodified PEG was unable to confer a non-adhesive or protein repellant character on such cells.

25

#### BRIEF DESCRIPTION OF THE INVENTION

In accordance with the present invention, we have developed methods to render cells non-adhesive and/or non-immunogenic with respect to macromolecules typically encountered in culture media or in physiological media.

The methods of the present invention can be used for a wide variety of purposes, e.g., for the treatment of cells used for implantation (thereby avoiding the need for immunosuppressive therapy), for the preservation of organs outside the body while awaiting transplant, for modifying surfaces of materials which are to be exposed to various

components of physiological media, for the stabilization of liposomes (and prevention of their uptake by the reticuloendothelial system), and the like.

5

#### DETAILED DESCRIPTION OF THE INVENTION

In accordance with the present invention, there is provided a method to render cells non-adhesive, said method comprising contacting said cells with an effective  
10 amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

As employed herein, reference to rendering cells "non-adhesive" means, in an *in vitro* setting, that cells do  
15 not stick to wells (e.g., glass, plastic, and the like), or other surfaces with which they come in contact. Instead, non-adhesive cells, as contemplated herein, spread and grow, yet remain in suspension. In an *in vivo* setting, "non-adhesive" refers to cells which do not adhere to  
20 biologically-encountered macromolecules or proteinaceous matrix (e.g., collagen matrix). As used herein, "non-adhesive" also refers to cells which have been rendered non-immunogenic, i.e., cells which are substantially non-susceptible to an immune response  
25 mediated by biological macromolecules.

"Contacting" of cells or tissues with graft copolymer compositions contemplated for use in the practice of the present invention is typically carried out *in vitro*  
30 at room temperature for a time in the range of about 0.01 up to 1 hour or longer in suitable physiological buffer (i.e., pH in the range of about 7.2-7.4; osmolarity of about 290 mOsm/kg) containing a concentration of at least about 0.005% of graft copolymer, with respect to the  
35 concentration of the polycationic species used for the preparation of the cell surface (e.g., polylysine). It is presently preferred to treat cells with a solution of graft

copolymer containing a concentration of graft copolymer in the range of about 0.05 up to 1.0%, with concentrations of graft copolymer in the range of about 0.1 up to 0.5% being especially preferred. Those of skill in the art recognize  
5 that as the molecular weight of the polycationic species is increased, a lower concentration (determined on the same basis as set forth above) of the graft copolymer is required to produce the same beneficial effect.

10 As employed herein, an "effective amount" of graft copolymer compositions contemplated for use in the practice of the present invention is an amount sufficient to render said cells non-adhesive to biological macromolecules, while leaving the cells viable (as  
15 determined, for example, by suitable staining techniques). In the case of specialized cells, such as islets, it is desirable for the treated cells to retain their unique function as well as viability (i.e., the ability of islets to respond to exposure to glucose by secretion of insulin).  
20 Typically, an excess of graft copolymer is used with respect to the negative charges present on the surface of the cells to be treated. The quantity of graft copolymer required will vary depending on the cell type being treated and the concentration of cells to be treated. Typically,  
25 in the range of about  $10^2$ - $10^8$  cells/ml will be treated. For example, up to about  $10^8$  bacterial cells/ml, up to about 100,000 fibroblasts/ml, or up to about 50,000 islets/ml will be treated.

30 Copolymer compositions contemplated for use in the practice of the present invention comprise a polycationic species having water-soluble polymer chains grafted thereon. Polycationic species contemplated for use in the practice of the present invention are polycationic  
35 species having sufficient charge density to allow binding of the above-described graft copolymer to cells, and include:

polymers containing primary amine groups, secondary amine groups, tertiary amine groups or pyridinyl nitrogen(s), such as polyethyleneimine, polyallylamine, polyetheramine, polyvinylpyridine, and the like,

polysaccharides having a positively charged functionality thereon (e.g., chitosan),

10 polyamino acids, such as:

poly-L-histidine, poly-im-benzyl-L-histidine, poly-D-lysine, poly-DL-lysine, poly-L-lysine, poly- $\epsilon$ -CBZ-D-lysine, poly- $\epsilon$ -CBZ-DL-lysine, poly- $\epsilon$ -CBZ-L-lysine,

poly-DL-ornithine, poly-L-ornithine, poly- $\delta$ -CBZ-DL-ornithine,

poly-L-arginine,

poly-DL-alanine-poly-L-lysine;

poly(-L-histidine, L-glutamic acid)-poly-DL-alanine-poly-L-lysine;

poly(L-phenylalanine, L-glutamic acid)-poly-DL-alanine-poly-L-lysine;

poly(L-tyrosine, L-glutamic acid)-poly-DL-alanine-poly-L-lysine;

random copolymers of:

L-arginine with tryptophan, tyrosine, or serine; D-glutamic acid with D-lysine;

L-glutamic acid with lysine, ornithine, or mixtures thereof;

and the like, as well as mixtures of any two or more thereof.

Presently preferred polycations for use in the practice of the present invention include polylysine (i.e., poly-D-lysine (PDL), poly-DL-lysine, poly-L-lysine (PLL), poly- $\epsilon$ -CBZ-D-lysine, poly- $\epsilon$ -CBZ-DL-lysine, or poly- $\epsilon$ -CBZ-L-lysine), polyornithine (i.e., poly-DL-ornithine, poly-L-ornithine or poly- $\delta$ -CBZ-DL-ornithine), and the like.

Polycationic species having a wide range of molecular weights can be employed in the practice of the present invention. Polycations having a MW in the range of about 200 up to 1,000,000 are suitable, with molecular weights in the range of about 1000 up to 100,000 preferred. Presently most preferred polycationic species for use in the practice of the present invention will have molecular weights in the range of about 5,000 to 50,000.

Optionally, the polycationic species employed in the practice of the present invention can be further modified with one or more functional groups capable of undergoing free radical polymerization. Suitable functional groups for this purpose include unsaturated species capable of free radical polymerization, such as, for example, acrylate groups, vinyl groups, methacrylate groups, and the like. When cells or tissues are treated with such modified polycationic species, the graft copolymer can be further subjected to free radical polymerization conditions, thereby stabilizing the association of graft copolymer with the cell surface. In addition, the further crosslinking of the graft copolymer forms a highly stabilized, immunoprotective coating of water-soluble polymer about the treated cell or tissue.



Free radical polymerization of the above-described modified polycationic species can be carried out in a variety of ways, for example, initiated by irradiation with suitable wavelength electromagnetic radiation (e.g., visible or ultraviolet radiation) in the presence of a suitable photoinitiator, and optionally, cocatalyst and/or comonomer. Alternatively, free radical polymerization can be initiated by thermal decomposition of a suitable free radical catalyst, such as benzoyl peroxide, azobisisobutyronitrile, and the like.

Photoinitiators contemplated for use in the practice of the present invention include such ultraviolet (UV) initiators as 2,2-dimethyl phenoxyacetophenone, benzophenones and ionic derivatives (for water solubility), benzils and ionic derivatives thereof, thioxanthenes and ionic derivatives thereof; and visible photoinitiators such as ethyl eosin, eosin, erythrosin, rose bengal, thionine, methylene blue, riboflavin, and the like.

Cocatalysts are typically used when the excited state of the photoinitiator is quenched too rapidly to efficiently promote polymerization. In such a situation, a cocatalyst (also referred to in the art as a "cosynergist", "activator", "initiating intermediate" or "quenching partner") will generally be employed. Cocatalysts contemplated for use in the practice of the present invention include triethanolamine, methyl diethanolamine, triethylamine, arginine, and the like.

Water-soluble polymeric species contemplated for use in the practice of the present invention are water-soluble polymers capable of rendering polycations non-immunogenic and include non-ionic, water-soluble polymers such as polyethylene glycol (PEG), polyvinyl alcohol (PVA), poly(hydroxyethyl methacrylate) (pHEMA), poly(acrylamide), poly(vinyl pyrrolidone) (PVP), poly(ethyl

oxazoline), polysaccharides (such as, for example, starch, glycogen, guar gum, locust bean gum, dextran, levan, inulin, cyclodextran, agarose, and the like); as well as ionic, water-soluble polymers such as polyacrylic acid (PAA) or polysaccharides (such as, for example, xanthan gum, carageenan, hyaluronic acid, heparin, chitosan, pectin, and the like); as well as copolymers of any two or more of said water-soluble polymeric species. Presently preferred water soluble polymers employed in the practice of the present invention are polyalkylene oxides, such as polyethylene glycol (PEG).

Water-soluble polymeric species having a wide range of molecular weights can be employed in the practice of the present invention. Polymeric species having a MW in the range of about 200 up to 1,000,000 are suitable, with molecular weights in the range of about 500 up to 100,000 preferred. Presently most preferred polymeric species for use in the practice of the present invention will have molecular weights in the range of about 1000 to 50,000.

Optionally, the water-soluble polymeric species employed in the practice of the present invention can be further modified with one or more functional groups capable of undergoing free radical polymerization. Suitable functional groups for this purpose include unsaturated species capable of free radical polymerization, such as, for example, acrylate groups, vinyl groups, methacrylate groups, and the like. When cells or tissues are treated with such modified water-soluble polymeric species, the graft copolymer can be further subjected to free radical polymerization conditions, thereby stabilizing the association of graft copolymer with the cell surface. In addition, the further crosslinking of the graft copolymer forms a highly stabilized, immunoprotective coating of water-soluble polymer about the treated cell or tissue.

Free radical polymerization of the above-described modified water-soluble polymeric species can be carried out in the same manner as described above with respect to free radical polymerization of modified polycationic species.

Graft copolymers contemplated for use in the practice of the present invention are those wherein the polycationic species has grafted thereon at least one water-soluble polymer chain per chain of said polycationic species, up to a maximum of one grafted chain per repeat unit of said polycationic species. For example, when the molecular weight of the polycationic species falls in the range of about 20,000, it will typically have grafted thereon at least about 5 chains of said water-soluble polymer chain per chain of polycationic species; with in the range of about 10-20 chains of said water-soluble polymer chain per chain of said polycationic species being the presently most preferred level of grafting. Those of skill in the art recognize that with polycationic species having higher molecular weights, higher levels of grafting will be desirable, and that the above values for grafting levels should be increased accordingly. Similarly, with respect to the water-soluble component of invention graft copolymers, the use of higher molecular weight species will allow one to achieve substantially the same result while grafting fewer (water-soluble) chains per chain of polycationic species.

Preparation of the graft copolymers of the present invention can be carried out employing chemical techniques known by those of skill in the art. For example, the free hydroxyl groups of the water-soluble component can be activated to render such groups susceptible to nucleophilic displacement. Thus, the free hydroxyl groups of the water-soluble component can be subjected to esterification, etherification, amidation,

urethane formation, and the like. Such reactions involve the generation of such intermediates as carbonates, sulfonates, xanthates, epoxides, aliphatic aldehydes, carboxymethyl azides, succinimidyl succinates, and the like. The activated water-soluble component can then be coupled to a suitable polycationic species, for example, by nucleophilic displacement.

Cell types contemplated for use in the practice of the present invention include islets, fibroblasts, thyroid cells, parathyroid cells, adrenal cells, neuronal cells, dopamine secreting cells, hepatocytes, nerve growth factor secreting cells, adrenaline/angiotensin secreting cells, norepinephrine/metencephalin secreting cells, human T-lymphoblastoid cells sensitive to the cytopathic effects of HIV, and the like.

Also included within the scope of the present invention are cells having a modified cell surface which is substantially non-adhesive with respect to macromolecules encountered in physiological environments.

In accordance with another embodiment of the present invention, there is provided a process to remove copolymer compositions contemplated for use in the practice of the present invention from cells treated as described above, said process comprising contacting such cells with an effective amount of an anionic species.

Anionic species contemplated for use in this embodiment of the present invention include monomeric or polymeric anions. Any soluble anionic species capable of reversing the association of polycationic species with negatively charged cell surface can be employed for this purpose. Presently preferred anionic species are polyanionic species, such as, for example, heparin, heparin sulfate, chondroitin sulfate, soluble alginates (e.g.,

sodium alginate, potassium alginate, ammonium alginate, and the like), bovine serum albumin, hyaluronic acid, pectin, carageenan, oxidized cellulose, and the like.

5               "Contacting" of treated cells to remove invention copolymer therefrom is carried out at room temperature for a time in the range of about 0.01 up to 1 hour or longer in physiological buffer solution containing anionic species at a sufficiently high ionic strength to reverse the  
10 association of polycationic species with negatively charged cell surface.

              An effective amount of anionic species to employ in accordance with this embodiment of the present invention  
15 depends on the specific anionic species employed. Generally, the concentration of anionic species employed will be sufficient to reverse polycation binding to cells or tissues, but not so high as to be toxic to the biological material being treated. Concentrations employed  
20 are typically in excess of the amount of anion actually needed to disrupt binding of polycation to cell surface. Thus, for example, presently preferred treating solutions contain about 2.5 Units/ml of heparin or 2 mg/ml of bovine serum albumin.

25

              In accordance with yet another embodiment of the present invention, there is provided a method to render cells non-immunogenic, said method comprising contacting said cells with an effective amount of a composition  
30 comprising a polycationic species having water-soluble polymer chains grafted thereon.

              "Contacting" of cells with graft copolymer compositions to render cells non-immunogenic is typically  
35 carried out as described above with respect to rendering cells non-adhesive.

The process of the present invention can be used for rendering non-immunogenic any cell, tissue, organ, or system of organs, and the like, that may be used for transplant or the like.

5

Also included within the scope of the present invention are cells having a modified cell surface which is substantially non-immunogenic with respect to mediators of immune response, e.g., biological macromolecules such as proteins, enzymes, and the like.

10

In accordance with another embodiment of the present invention, there is provided a process to remove copolymer compositions contemplated for use in the practice of the present invention from cells treated as described above, said process comprising contacting treated cells with an effective amount of an anionic species, as described above.

15

In accordance with still another embodiment of the present invention, there is provided a method to preserve cells and/or tissues which are subjected to long periods of storage before being used for therapeutic applications, said method comprising contacting said cells and/or tissues with an effective amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

20

25

"Contacting" of cells and/or tissues with graft copolymer compositions to preserve same is typically carried out as described above with respect to rendering cells non-adhesive and/or non-immunogenic.

30

In accordance with a still further embodiment of the present invention, there is provided a method for associating water-soluble polymer with a cell surface, said method comprising:

35

grafting water-soluble polymer onto a polycationic resin to produce a copolymer of said water-soluble polymer and said polycation, and thereafter

5           contacting said cell surface with an effective amount of said copolymer.

If desired, the copolymer can be substantially removed from the cell surface employing the above-described  
10 removal process.

In accordance with a further embodiment of the present invention, there is provided a method for the stabilization of liposomes having negatively charged  
15 surfaces, said method comprising contacting said liposomes with an effective, stabilizing amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

20           "Contacting" of liposomes for the stabilization thereof is carried out at room temperature for a time in the range of about 0.01 up to 1 hour or longer in physiological buffer.

25           An effective amount of graft copolymer for use in this embodiment of the present invention is an amount sufficient to render such liposomes essentially non-detectable *in vivo*, thereby reducing uptake of the liposome by the reticuloendothelial system (and increasing  
30 liposome circulation times *in vivo*). Suitable quantities of graft copolymer will render the liposomes substantially non-adhesive to biological materials, while leaving the liposome intact, and without adversely affecting the function and/or activity of the contents thereof, if any.  
35 Typically, a concentration of graft copolymer sufficient to neutralize the negative charges on the surface of the liposome will be employed. Concentrations in the range of

at least about 0.05% of graft copolymer, with respect to the concentration of the polycationic species used to treat the surface of said liposome will be employed; with concentrations of graft copolymer in the range of about 0.1  
5 up to 0.5% being presently preferred.

One can readily determine the stability of a liposome using a functional assay, such as the following. In an *in vitro* setting, the stability of liposome-  
10 encapsulated hemoglobin in an un-modified liposome could be compared to the stability of hemoglobin encapsulated in a liposome stabilized in accordance with the present invention (i.e., the result of treating an un-modified  
15 liposome with a sufficient quantity of graft copolymer described above to stabilize the liposome). The release of hemoglobin into the surrounding buffer media over time would then be assayed, with an extended time-frame for release of hemoglobin indicating enhanced liposome  
20 stability.

In accordance with yet another embodiment of the present invention, there is provided a method for producing neural networks on a substrate, said method comprising:

masking that portion of said substrate which  
25 defines the desired network,

rendering the unmasked portion of said substrate non-adhesive by the above-described method of the invention,

removing the mask, then  
30 allowing cells to spread and grow on said substrate, wherein cells grow only on the portion of the substrate which has not been treated with graft copolymer.

Substrates contemplated for use in the above-  
35 described method include tissue culture substrates, such as collagen, tissue culture polystyrene, microporous dextran substrate, and the like.



Masking contemplated by the above-described method can be accomplished in a variety of ways, such as, for example, by covering a portion of the substrate with an agent which does not serve as a substrate for cell growth (e.g., a piece of tape, or the like).

The masking agent employed can readily be removed by merely reversing the process employed for applying the mask to the substrate.

Conditions required for cells to spread and grow on the substrate are standard cell culture conditions.

The resulting neural networks can be used for a variety of purposes, such as, for example, for studying the transmission of nerve impulses, for connection between a nerve cell and an electrical circuit, and the like.

The invention will now be described in greater detail by reference to the following non-limiting examples.

#### EXAMPLES

##### EXAMPLE I

##### Synthesis of a Graft copolymer of Poly-L-Lysine and Polyethylene Glycol

Twenty grams (20 g) of PEG (molecular weight 10,000 g/mol, having the structure HO-PEG-OH) were dried in a vacuum oven at 80°C for 24 hours and dissolved in 100 ml of methylene chloride that had been dried by molecular sieves (4A). Then, 3.24 g of 1,1-carbonyldiimidazole (CDI, 5 fold excess, to ensure the activation of 100% of PEG end groups) were added to the solution and stirred overnight at room temperature in an argon atmosphere. The CDI-activated PEG was then precipitated with an excess of anhydrous diethyl ether and dried overnight under vacuum. Five grams

(5 g) of the CDI-activated PEG were dissolved in 20 ml of 5 mM sodium borate buffer (pH 9). In order to prevent crosslinking of poly-L-lysine (PLL) with the 100% CDI-activated PEG, 50% of the PEG end groups were  
5 inactivated by adding 30.2  $\mu$ l of ethanolamine to the buffer solution and stirring for 4-6 hours at room temperature. This results in a mono-activated CDI-derivative of PEG, having the structure CDI-PEG-OH. Alternatively, a monomethoxy PEG could be used to avoid this partial  
10 deactivation step, but monomethyl PEGs are presently available commercially only up to molecular weight 5000.

Following the above-described partial deactivation step, 50 mg of PLL (M.W. 20,100 g/mol) were  
15 added to the reaction mixture and stirred for 24 hours at room temperature. The solution was then dialyzed for 24 hours against deionized water and freeze dried to obtain a powder. This procedure produced a PEG graft copolymer (PLL-PEG) having a concentration of approximately 10-20 PEG  
20 chains per PLL chain.

## EXAMPLE II

### Demonstration of Cell Binding Properties of PLL-PEG to Fibroblasts: Effect on Cells in Suspension

25

The cell binding effects of PLL-PEG copolymer produced as described in Example I were tested on cultures of human foreskin fibroblasts (HFF). These cells are anchorage dependent and ordinarily die within 4 to 10 hours  
30 if they do not adhere and spread on a surface. Thus, a flask of confluent HFF was harvested with trypsin-EDTA, then the resultant cells in suspension were split into 6 batches, each containing approximately 170,000 cells. Each batch was centrifuged to obtain cell pellets. Six  
35 different solutions were used for cell treatment:

- (A) Fibroblast culture media: Dulbecco's modified Eagles' medium (D-MEM) containing 10% fetal bovine serum;
- (B) 10 mM HEPES buffered saline (HBS), pH 7.4;
- 5 (C) HBS containing 0.1% (w/v) PLL;
- (D) HBS containing 0.5% PEG (M.W. 10,000);
- (E) HBS containing 0.1% PLL and 0.5% PEG; and
- (F) HBS containing 0.3% PLL-PEG (based on PLL concentration).

10

All solutions were sterilized by filtration through 0.22 micron filters prior to use. The cell pellets were resuspended in 2 ml of solutions A, B, C, D, E or F for approximately 10 minutes. The tubes were then centrifuged

15 (200 xg for 5 minutes), the solutions aspirated and replaced with fibroblast culture medium, and the cells plated onto culture dishes. The plated cells were observed periodically to verify adherence and spreading. The cells were also stained with trypan blue (TB) to test viability.

20 Table I summarizes the observations over 5 days following the seeding.

TABLE I  
HFF TREATMENT SOLUTIONS

TIME AFTER SEEDING	A (fibroblast culture medium)	B (buffered saline)	C (PLL)	D (PEG)	E (PLL + PEG)	F (PLL-PEG copolymer)
1 hr	Normal spreading	Normal spreading	No adherence; Cell clumping	Normal spreading	No adherence; Cell clumping	No adherence; No clumping
% viability	95	95	0	90	0	80
24 hr	Normal spreading	Normal spreading	No adherence; Cell clumping	Normal spreading	No adherence; Cell clumping	No adherence; No clumping
% viability	100	100	0	95	0	70

TABLE I (cont.)

## HFF TREATMENT SOLUTIONS

TIME AFTER SEEDING	A (fibroblast culture medium)	B (buffered saline)	C (PLL)	D (PEG)	E (PLL + PEG)	F (PLL-PEG copolymer)
48 hr	Confluent monolayer	Confluent monolayer	No adherence; Cell clumping	Confluent monolayer	No adherence; Cell clumping	No adherence; No clumping
% viability	100	100	0	95	0	60
120 hr	Confluent monolayer	Confluent monolayer	No adherence; Cell clumping; Few spread Cells	Confluent monolayer	No adherence; Cell clumping; Few spread Cells	No adherence; No clumping; Few spread Cells
% viability	100	100	<1	95	<3	60

Treatments A, B, and D showed essentially the same results, with most of the HFF showing normal spreading and viability.

5 Free PLL was found to be toxic at the concentrations used (treatments C and E). Essentially all cells subjected to treatments C and E took up TB and did not spread on the tissue culture substrate. The cells subjected to treatments C and E also showed extensive  
10 aggregation.

Free PEG had no appreciable effect on cell function (treatment D). PEG also had no appreciable ameliorating effect in conjunction with PLL (treatment E).  
15

Incubation with the graft PLL-PEG copolymer of the present invention (treatment F) however, had a remarkable effect on the HFF. In stark contrast to treatment with free PLL, treatment with the copolymer  
20 PLL-PEG (at 3 times higher concentration than used for treatments C and E) produced cells that showed no adherence to the substrate, no aggregation in suspension, but a high percent viability. This viability was maintained for well over 24 hours with the HFF still in suspension. This  
25 behavior is quite unusual for anchorage dependent cells.

A distinct morphological difference in cells treated with PLL and PLL-PEG was evident. PLL treated cells in suspension showed a rough or ragged surface while  
30 those treated with PLL-PEG copolymer of the present invention are smooth and spherical, much like freshly trypsinized cells.

These results indicate that treatment with the  
35 PLL-PEG copolymer of the invention is noncytotoxic to HFF. In addition, interaction of the PEG-grafted polycation with the exterior of the cell prevents the cell from adhering to

a substrate. Thus the cytotoxicity of PLL is markedly reduced by PEG grafting.

Five days after the initial treatment, a few of the cells treated with PLL-PEG copolymer begin to show some spreading on the surface of the culture dish. This observation implies that the PLL-PEG copolymer may either have desorbed from the cell surfaces, or cell division may have occurred (which would dilute the concentration of PLL-PEG copolymer on the cell membrane).

### EXAMPLE III

#### Assessment of Efficacy of PLL and PLL-PEG Treatments at Various Dilutions

15

A similar experiment as outlined in Example II was conducted to test the effects of PLL and PLL-PEG copolymer at various dilutions. Solutions C and F were serially diluted with 10 mM HEPES buffered saline (HBS) to 1/5, 1/25, and 1/125 of their original concentrations, and human foreskin fibroblasts (HFF) incubated in these solutions for 10 minutes. Additional treatments included PEG 20M (a PEG composition having a molecular weight of about 20,000, comprised of two lower molecular weight PEGs (one having a MW ~8,000 and the other having a MW of ~10,000) linked together by a hydrophobic, bifunctional bisphenol-epichlorohydrin linker; available from Union Carbide, Danbury, CT) and PEG 20,000 (a substantially linear PEG having a molecular weight of ~20,000; available from Fluka, Ronkonkoma, NY) at 0.5% in HBS. A control treatment with fibroblast culture media was also run. Results are summarized in Table II, below.

In the Table, the following abbreviations are used:

"adh." for adhesion,  
"aggreg." for aggregated, and  
"subst." is the abbreviation for substrate.

5 P-0 refers to cells treated with 0.1% of PLL, and P-5, P-25  
and P-125 refer to cells treated with 1/5, 1/25, and 1/125  
dilutions thereof, respectively. Similarly, G-0 refers to  
cells treated with 0.3% of PLL-PEG copolymer, and G-5, G-25  
and G-125 refer to cells treated with 1/5, 1/25, and 1/125  
10 dilutions thereof, respectively.



TABLE II

## HFF TREATMENT SOLUTIONS

TIME AFTER SEEDING	Control		PLL treatment				PLL-PEG copolymer treatment			
	No PEG	20M PEG	20,000 PEG	P-0	P-5	P-25	P-125	G-0	G-5	G-25 G-125
0 hr	-----	Minor adh. to substr.	-----	Clumped	Clumped	Clumped	Clumped; adh. to subst.	No adh.	No adh.	Minor adh. to adh. subst. Minor adh. to adh. subst.
3 hr	-----	100% adh. to subst.	-----	Clumped; aggreg.; no adh. to subst.	Clumped; aggreg.; no adh. to subst.	Clumped; 5-10% adhered to subst.	Clumped; 5-10% adhered to subst.	No adh.	50% adh.	75% adh. to subst. 100% adh. to adh. subst.
24 hr	-----	100% adhesion	-----	No adh; Extensive clumping	No adh; Extensive clumping	Clumped; ~10% adh. to subst.	Clumped; ~10% adh. to subst.	No adh.	~60% adh.; no clumping	~80% adh. ~100% adhesion
% viability	-----	100%-----	-----	<10%	<10%	<10%	<10%	>70%	>70%	>70%

Observation of the cells immediately after seeding showed all PLL treatments (abbreviated P) to cause clumping of cells. A small number of cells showed adherence in the P-125 treatment. The graft copolymer (PLL-PEG, abbreviated G) treatment showed a decrease in efficacy at the lower concentrations. At dilutions of 25 and 125 (G-25 and G-125), adherence of cells was noted, though not quantified. Treatments with the PEG 20M and PEG 20,000 showed no appreciable difference from the control.

Three hours following the initial seeding, the following observations were made. The PLL treated cells P-0 (0.1% PLL) and P-5 were clumped and aggregated, with none of the cells showing adherence to the substrate. P-25 and P-125 also showed clumping, but approximately 5-10% of cells adhered to the substrate, indicating PLL cytotoxicity at very low concentrations.

Cells treated with PLL-PEG showed an increased adhering tendency with increasing dilutions. G-0 (0.3% PLL-PEG) showed no adhesion and individual free-floating cells. G-5, G-25, and G-125 showed approximately 50%, 75% and 100% adherence, respectively, at 3 hours. G-125 was very similar to the PEGs and the control.

After 24 hours, P-0 and P-5 showed no adherence to substrate, and extensive clumping. P-25 and P-125 also showed clumping, but approximately 10% of the cells were adhered to the substrate, indicating a lower level of toxicity for P-25 and P-125, compared to the higher concentrations used in samples P-0 and P-5.

After 24 hours, G-0 showed no adherence to substrate and no clumping; while G-5, G-25 and G-125 showed increasing levels of adherence of approximately 60%, 80% and 100%, respectively. The PEG treatments and the control

were also 100% adhered.

TB staining at 24 hours showed all PLL treatments to have less than 10% viability, while the treatments with  
5 PLL-PEG copolymer showed a viability of greater than 70%. Thus the attachment of PEG to PLL substantially alleviates the PLL toxicity; this effect is apparent at very low concentrations (P-125 = 0.0008% PLL; G-125 = 0.0024%).

10

## EXAMPLE IV

Effect of PLL and PLL-PEG on Confluent Monolayers  
of Fibroblasts

In order to assess, in a more realistic (although  
15 in vitro situation), the effects of PLL and PLL-PEG copolymer of the invention on cells which would normally be present in a flattened spread morphology (and not in a rounded morphology), confluent monolayers of HFF were treated with solutions P-0, P-5, G-0, G-5, PEG 20M, and a  
20 control (fibroblast culture medium). The cells were exposed to these solutions for 10 minutes, followed by a rinse with HBS, then fibroblast culture medium was returned to the culture dishes.

25 Short-term observation 15 minutes after treatment showed the P-0 treated cells sloughing off the culture substrate, with approximately 90% of all cells in suspension at 20 minutes.

30 About 2-5% of cells treated with P-5 were detached from the surface within the same 15 minute period.

HFF treated with solutions G-0, G-5 and PEG 20M showed no appreciable difference from the control cells.

35

These results indicate that PLL (at 0.1%) is clearly toxic to HFF, while similar concentrations of PLL

modified with PEG show no harmful effects to confluent monolayers of cells. It is noteworthy that the P-5 treatment showed only mild toxicity to spread, confluent fibroblasts, indicating that they may be less susceptible to toxic macromolecules in this state rather than in suspension.

#### EXAMPLE V

##### Reversal of PLL-PEG Binding to Cells with Polyanions

10

It was possible, by addition of heparin sulfate or chondroitin sulfate, to reverse the effect of PLL and PLL-PEG on HFF. Thus, addition of 2.5 U/ml of heparin to the fibroblast culture medium soon after treatment with PLL caused disaggregation of the HFF clumps and resulted in cells that were able to adhere to tissue culture substrates. If, however, the addition of heparin was postponed until several hours after the PLL treatment, reversibility was not possible because the cells had succumbed to PLL toxicity.

This however, was not the case with the PLL-PEG copolymer if the present invention. The nonadhesive, nonaggregating nature conferred upon the fibroblasts by treatment with PLL-PEG copolymer was found to be reversible at least 48 hours after the initial treatment, clearly indicating that these anchorage dependent cells were still alive, despite the fact that they were not adhered to a substrate.

30

#### EXAMPLE VI

##### Resistance of PLL-PEG Treated Cells to Specific Antibodies as Indicators of Conferred Immune Protection

Fibroblasts have receptors for the protein vitronectin on their surfaces. Vitronectin is a cell adhesion molecule (CAM). This receptor (called  $\alpha V\text{-}\beta 3$ ) can

35

be targeted with an antibody, anti  $\alpha$ V-B3, a rabbit polyclonal. A fluorescently conjugated secondary antibody to anti  $\alpha$ V-B3 (e.g., rhodamine conjugated anti IgG, goat anti-rabbit) would permit the visualization of these  
5 receptors on the cell surface.

Untreated HFF, PLL treated HFF, and PLL-PEG treated HFF were incubated with anti  $\alpha$ V-B3 polyclonal antibody, followed by incubation with the secondary  
10 antibody, then observed at the appropriate excitation wavelengths under a microscope. It was observed that the untreated and PLL treated cells showed strong fluorescence, while the PLL-PEG treated cells fluoresced at a much lower level. This observation indicates that the approach of the  
15 antibody to the cell is hindered by the presence of PEG.

PLL by itself was found not to affect the receptor-ligand interaction.

20 Based on the above-described experiments, it is likely that the prevention of protein binding to these cells will render them immunologically unrecognizable.

#### EXAMPLE VII

##### 25 Transplantation of PLL-PEG Treated Allogeneic Islets in Rats as a Model for Immunoprotectivity

Rat islets were isolated employing techniques known in the art [see, for example, Lacy and Kostianovsky  
30 in Diabetes 16:35 (1967)]. The isolated islets were treated with 0.3% PLL-PEG as described above (see Example II), and transplanted by injection into the peritoneal cavity of diabetic rats. Diabetes was induced by treatment with streptozotocin. Controls were injected with untreated  
35 rat islets. Blood glucose levels of these rats were monitored at first on an hourly basis, and then on a daily basis for several weeks. It was found that the control

rats had a reversal of diabetes (indicated by normal glucose levels) for 3-4 days following which the graft failed due to rejection. On the other hand, the rats injected with the PLL-PEG copolymer treated islets showed  
5 a continuous reversal of diabetes for several weeks, indicating that the treatment of these cells with PLL-PEG copolymer was effective in immunoprotecting the islets.

#### EXAMPLE VIII

10

#### Crosslinkable Graft Copolymers

A variation on the above theme for the surface treatment of cells is one in which the PLL-PEG graft copolymer has on its structure polymerizable groups such as  
15 the acrylate group. The presence of this group on the graft copolymer facilitates polymerization or crosslinking following the absorption of the copolymer onto the cell surface through ionic interactions. The resultant covalently crosslinked network is significantly more stable  
20 than the ionically attached graft copolymer. Thus the immunoprotective properties conferred upon the cell by absorption of PLL-PEG on its surface are no longer transient as may be expected through an ionic interaction, but are permanent due to the formation of intermolecular  
25 and intramolecular covalent crosslinks formed with the PLL-PEG.

Synthesis of these polymerizable copolymers could have two possible strategies. One involves the synthesis  
30 of a PEG that is heterobifunctional, i.e., one end is functionalized with CDI (1,1-carbonyldiimidazole; or other electrophilic derivative) and the other with acryloyl chloride (the reaction of PEG with acryloyl chloride is described below). This technique allows the synthesis of  
35 a PLL-PEG graft copolymer in which the free end of PEG contains a polymerizable double bond. The second strategy involves the preparation of PLL-PEG as described above, and

the subsequent reaction of the copolymer with acryloyl chloride to add polymerizable groups. In this case the addition of polymerizable groups to the copolymer is nonspecific, i.e., the substitution occurs on the free end  
5 of the PEG as well as on the amines on polylysine.

The reaction of PEG with acryloyl chloride proceeds to completion in about 24 hours when carried out at 50°C. For example, mono-CDI functionalized PEG (i.e.,  
10 CDI-PEG-OH, prepared as described in Example I) was reacted with an equimolar amount of acryloyl chloride in dry dichloromethane solvent. The reaction was carried out in a round-bottom flask under an inert atmosphere at constant reflux for 24 hours. The resulting product was purified by  
15 precipitation with diethyl ether, then dried in a vacuum oven.

Alternatively, PLL-PEG could be treated with acryloyl chloride. In this situation, acrylate  
20 substitution would occur on both the PEG chains and the PLL backbone (via the amine groups thereof).

Photopolymerization is the method of choice for covalent crosslinking of the graft copolymer following  
25 attachment to the cell surface. Following attachment of the graft copolymer to the cell surface the treated cells are transferred to a physiological buffer solution containing ethyl eosin (EE, 0.1  $\mu$ M to 0.1 mM), triethanolamine (TEA, 0.1 mM to 0.1 M), and optionally a  
30 comonomer (e.g. 1-vinyl 2-pyrrolidinone (VP) at a concentration in the range of about 0.001 to 1.0%, when used). This solution containing islets is well mixed and exposed to a mercury lamp (100 watt) with a bandpass filter (500-560 nm) for approximately 3 minutes. This causes  
35 crosslinking of the copolymer on the surface of the cell resulting in the immunoprotective layer. The cells are then transferred to culture.

An alternative technique involves the incubation of the copolymer treated cells with a solution of EE (0.1  $\mu$ M to 0.1 mM) in physiological buffer for approximately two minutes. In this step the EE complexes with the positively charged polycation on the cell surface. After rinsing in buffer the cells are transferred to a physiological buffer solution containing TEA (conc. as above), and a comonomer e.g. VP (optional). This solution containing islets is well mixed, polymerized as before, and transferred to culture.

#### EXAMPLE IX

##### PLL-PEG Solutions in Organ Preservation Media

As noted above, PEG 20M has been used in the preservation of organs. The basis of its activity, though not clearly understood, is believed to be the binding of PEG to cell surface molecules through nonspecific hydrophobic interactions. The PLL-PEG copolymer of the present invention, however, interacts directly through ionic interactions with cell-surface moieties bearing a negative charge. Thus, tissues and organs may be flushed with a solution containing the PLL-PEG copolymer prior to transplantation to, in effect, 'coat' the tissues with PEG, thereby providing an immunoprotective and organ-protective effect.

#### EXAMPLE X

##### Stabilization of Liposomes with PLL-PEG for Longer Circulation Times and Increased Biocompatibility

Lipid vesicles or liposomes have been investigated extensively as systems for drug delivery (Gregoriadis, 1987). The commonly used phospholipids that comprise liposomes, such as phosphatidyl choline, phosphatidyl serine, dilaurylphosphatidic acid, and phosphatidylglycerol are negatively charged at



physiological pH. The interaction of polycations such as PLL with the negatively charged phospholipids has been studied quite extensively with regard to conformational changes induced in PLL and consequent stability [Fukushima et al., *Biophysical Chemistry* 34:83 (1989); Houbre et al., *Biophysical Chemistry* 30:245 (1988)]. Stability of liposomes in physiological conditions is a major focus of researchers investigating drug delivery. Although PLL may be used to stabilize lysosomes *in vitro*, PLL coated liposomes *in vivo* are likely to be rapidly overgrown or ingested by macrophages due to the adhesive nature of PLL, thus making them ineffective for the controlled release of drugs. In addition, liposomes may also be destroyed by uptake by the reticuloendothelial system. The addition of the graft copolymers of the present invention to the surface of the liposome is likely to prevent this uptake.

The replacement of PLL by the PLL-PEG copolymer of the present invention, however, promises to provide a liposome that is stable not only due to interactions between negatively charged phospholipid and positively charged PLL, but also because the PLL-PEG copolymer will prevent interactions with proteins, and therefore prevent interactions with cells such as macrophages. This should result in liposomes with long circulation times which can therefore deliver drugs in a controlled fashion.

#### EXAMPLE XI

##### Patterned Surfaces for Neural Networks

30

Investigators in neurology have tried to generate *in vitro* networks of neurons on culture dishes. A problem has been to generate patterned surfaces that are preferentially adherent to cells in order to design 'biological circuits.' By creating a mask of the pattern desired, and applying it to the culture substrate, followed by treatment of the surface with PLL-PEG copolymer, one can

selectively leave the desired pattern adhesive to cells, while the rest of the available surface is rendered nonadhesive to cells.

- 5           While the invention has been described in detail with reference to certain preferred embodiments thereof, it will be understood that modifications and variations are within the spirit and scope of that which is described and claimed.

That which is claimed is:

1. A method to render cells non-adhesive, said method comprising contacting said cells with an effective amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.
2. A method according to claim 1 wherein said water-soluble polymer is selected from polyethylene glycol (PEG), polyvinyl alcohol (PVA), poly(hydroxyethyl methacrylate) (pHEMA), polyacrylic acid (PAA), poly(acrylamide), poly(vinyl pyrrolidone) (PVP), poly(ethyl oxazoline) (PEOX), polysaccharides, or copolymers of any two or more thereof.
3. A method according to claim 1 wherein said polycationic species has grafted thereon at least one water-soluble polymer chain per chain of said polycationic species.
4. A method according to claim 3 wherein said water-soluble polymer is polyethylene glycol.
5. A method according to claim 1 wherein either the water-soluble polymer, or the polycationic species, or both contain at least one functional group which is susceptible to free radical polymerization.
6. A method according to claim 5 wherein said composition is further subjected to free radical polymerization conditions.

7. A method according to claim 1 wherein said polycationic species is selected from:

polyethyleneimine, polyallylamine, polyetheramine,  
5 polyvinylpyridine,

polysaccharides having a positively charged functionality thereon,

10 polyamino acids selected from:

poly-L-histidine, poly-im-benzyl-L-histidine,  
poly-D-lysine, poly-DL-lysine, poly-L-lysine,  
poly- $\epsilon$ -CBZ-D-lysine, poly- $\epsilon$ -CBZ-DL-lysine,  
poly- $\epsilon$ -CBZ-L-lysine,

15

poly-DL-ornithine, poly-L-ornithine,  
poly- $\delta$ -CBZ-DL-ornithine,

poly-L-arginine,

20

poly-DL-alanine-poly-L-lysine;

poly(-L-histidine, L-glutamic  
acid)-poly-DL-alanine-poly-L-lysine;

25

poly(L-phenylalanine, L-glutamic acid)-  
poly-DL-alanine-poly-L-lysine; or

poly(L-tyrosine, L-glutamic acid)-  
poly-DL-alanine-poly-L-lysine;

30

random copolymers of:

L-arginine with tryptophan, tyrosine, or serine;  
D-glutamic acid with D-lysine; or

35

L-glutamic acid with lysine, ornithine, or  
mixtures thereof;

as well as mixtures of any two or more thereof.

8. A method according to claim 1 wherein said polycationic species is selected from polylysine or polyornithine.

5 9. A method according to claim 1 wherein said cells to be rendered non-adhesive are selected from islets, thyroid cells, adrenal cells, dopamine secreting cells, hepatocytes, or human T-lymphoblastoid cells sensitive to the cytopathic effects of HIV.

10 10. The cellular product obtained by the method of claim 1.

15 11. A process to remove composition(s) comprising a polycationic species having water-soluble polymer chains grafted thereon from cells treated in accordance with the method of claim 1, said process comprising contacting said treated cells with an effective amount of an anionic species.

20 12. A process according to claim 11 wherein said anionic species is monomeric or polymeric.

25 13. A process according to claim 12 wherein said anionic species is a polyionic species selected from heparin, heparin sulfate, chondroitin sulfate, bovine serum albumin, soluble alginates, hyaluronic acid, pectin, carageenan, or oxidized cellulose.

30 14. Cells having a modified cell surface which is non-adhesive with respect to mediators of immune response, wherein the surface of said cells have been modified with a composition comprising a polycationic species having water-soluble polymer chains grafted  
35 thereon.

15. A method to render cells non-immunogenic, said method comprising contacting said cells with a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

5

16. A method according to claim 15 wherein said polycationic species has grafted thereon at least one water-soluble polymer chain per chain of said polycationic species.

10

17. A method according to claim 16 wherein said water-soluble polymer is polyethylene glycol.

18. A method according to claim 15 wherein said cells to be rendered non-immunogenic are selected from islets, thyroid cells, adrenal cells, dopamine secreting cells, hepatocytes, or human T-lymphoblastoid cells sensitive to the cytopathic effects of HIV.

15

19. The cellular product obtained by the method of claim 15.

20. A process to remove composition comprising polycationic species having water-soluble polymer chains grafted thereon from cells treated in accordance with the method of claim 15, said process comprising contacting said treated cells with an effective amount of an anionic species.

20

25

21. A method to preserve cells and/or tissues which are subjected to long periods of storage before being used for therapeutic applications, said method comprising contacting said cells and/or tissues with an effective amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

22. A method for associating water-soluble polymer with a cell surface, said method comprising:  
grafting water-soluble polymer onto a polycationic resin to produce a copolymer of said water-soluble polymer and said polycation, and thereafter  
contacting said cell surface with an effective amount of said copolymer.

23. A method according to claim 22 wherein said copolymer comprises a polycation having grafted thereon at least one water-soluble polymer chain per chain of said polycationic resin.

24. A method for the stabilization of liposomes having negatively charged surfaces, said method comprising contacting said liposomes with an effective, stabilizing amount of a composition comprising a polycationic species having water-soluble polymer chains grafted thereon.

25. A method according to claim 24 wherein said polycationic species has grafted thereon at least one water-soluble polymer chain per chain of said polycationic species.

26. A method for producing neural networks on a substrate, said method comprising:

masking that portion of said substrate which defines the desired network,

5 rendering the unmasked portion of said substrate non-adhesive by the method of claim 1,

removing the mask, then

allowing cells to spread and grow on said substrate.



## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US93/02609

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(5) :A01N 1/02; C12P 1/00; C12N 5/00

US CL :435/1, 41, 240.1, 240.22, 962

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 435/1, 41, 240.1, 240.22, 962

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

CAS ONLINE, APS, BIOSIS, EMBASE, MEDLINE

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO, A, 91/07951 (Skjak-Braek et al.) 13 June 1991, see page 3 and claim 10.	1-10
Y	Neuroscience Letters, Volume 49, issued 1984, U. T. Ruegg et al., "Growth of Dissociated Neurons in Culture Dishes Coated with Synthetic Polymeric Amines," pages 319-324, see page 319.	1-10
Y	Transplantation, Volume 51, No. 1, issued January 1991, Tianli Zheng et al., "Prolonged Pancrease Preservation Using A Simplified UW Solution Containing Polythylene Glycol", pages 63-66, see page 63, abstract.	1-10



Further documents are listed in the continuation of Box C.



See patent family annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be part of particular relevance

\*E\* earlier document published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\*

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\*

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\*

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

\*Z\*

document member of the same patent family

Date of the actual completion of the international search

12 May 1993

Date of mailing of the international search report

08 JUN 1993

Name and mailing address of the ISA/US

Commissioner of Patents and Trademarks

Box PCT

Washington, D.C. 20231

Facsimile No. NOT APPLICABLE

Authorized officer

RALPH GITOMER

Telephone No. (703) 308-0196

## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US93/02609

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	Journal of Biomedical Materials Research, Volume 25, issued 1991, Neil P. Desai et al., "Biological Responses to Polyethylene Oxide Modified Polyethylene Terephthalate Surfaces", pages 829-843, see page 829, abstract.	1-10